



**SHALIMAR
PAINTS**

TUFFKOTE

PROTECTIVE COATINGS

EPIGARD 63 ZP

Data Sheet No. SPL/PMG/201910001511

A two pack epoxy primer containing Zinc phosphate pigment. The red version contains red oxide of iron along with zinc phosphate. The primer gives excellent adhesion to steel. It is compatible with a wide range of topcoats. This coating when applied with proper intermediate and topcoat provide highly efficient protective system for corrosive environments.

Product Information

Colour	Selected Range
Finish	Eggshell to Semi gloss
Flash Point	Above 23°C
Mixing Ratio (By Volume)	Base : Accelerator 4 : 1
Volume Solids	65±3%
Recommended dry film thickness	100 - 125 microns
Corresponding wet film thickness	154 – 192 microns
Theoretical Spreading Rate	6.5 – 5.2 Sq.m/ltr
Drying time @ 30° C	Surface dry 1 - 2 hours Full cure 7 days
Interval before Over-coating	Minimum 2-4 hours Maximum 7 days
Volatile Organic compound (VOC)	280 gm/ltr (EPA Method 24)
Storage Life	Up to 12 months so long as the material is stored in a sealed containers under standard warehouse storage conditions
Dry Heat Resistance	Up to 150°C (Intermittent)

Surface Preparation

Steel Surface

Surface must be clean, dry & free from contamination. Prior to paint application, all surfaces should be assessed and treated in accordance with ISO 8504:2000.

Abrasive blast clean to Sa 2½ is recommended.

If abrasive blast cleaning is not possible it is recommended to hand tool/power tool clean to St2 or St3 before application of this product.

For Damage area rectification contact the Technical team of Shalimar Paints Limited

Application Details

Method of Application

Air Spray / Airless Spray / Brush / Roller

Notes on Airless Spray

Tip Range	15 – 21 thou.
Total Output	2500 - 3500 psi.
Fluid Pressure	(176 - 246 kg/sq.cm.)
Pot Life	4 to 8 hours
Thinner	Thinner 6756

Notes on Air Spray

Nozzle Orifice – 1.2 mm to 1.6 mm
Nozzle Pressure – 0.3-0.4 Mpa

Uses

Suitable as primer for fertilizer, Refineries, Petrochemicals, Pulp & Paper, Chemicals and other industries where high performance coating system are required.

System Selection Guide

SURFACE	1 ST COAT	2 ND COAT	3 RD COAT	4 th Coat
Steel	EPIGARD 63 ZP	Epigard 80 MIO	Shalithane 57UV	Shalithane 57UV

Chemical Resistance Guide (with suitable top coat)

EXPOSURE	Acids	Alkalis	Solvents	Salt	Water
SPLASH & SPILLAGE	Fair	Fair	Very Good	Very Good	Very Good
FUMES & OUTDOOR EXPOSURE	Good	Good	Very Good	Very Good	Very Good

Health & Safety

Use Proper Personal Protective Equipment(PPE) during application of this product.

Please consult Material Safety Datasheet (MSDS)

Precaution

Provide adequate ventilation during application and drying. Clean Spray gun equipment and hose immediately after application of material.

Standard Pack Size

20 litres - For available pack size contact local representative of Shalimar Paints Limited

NOTES:

1. This Product datasheet supersedes all previous datasheet and subject to change without prior notice
2. Do not apply when surface temperature is less than 3 °C than dew point.
3. Mixing with mechanical agitator is strongly recommended
4. Use material within stipulated pot life
5. Do not apply paints when environment temperature rises above 50 °C or when relative humidity rises above 85%. Do not apply during rain, fog or mist.
6. Use of thinners other than supplied or approved by Shalimar may adversely affect product performance
7. Drying is dependent on temperature, relative humidity and thickness; ranges is given for considering those parameters
8. System Guide is a typical and for indicative purpose only, however this can have wide range of combination. For details, please contact Shalimar Paints limited
9. Request for details information of surface preparation, paint application on the recommended coating system

DISCLAIMER: This PDS is by no means a comprehensive data. The company will not be liable for losses or damages howsoever caused including liability for negligence, which may be suffered by the user of the data contained therein. It is the user's responsibility to conduct all necessary tests to confirm the suitability of any product or system for their intended use. No guarantee of result is extended since conditions of use are beyond our control. Liability is limited to replacement of the product hence cost of labour charges or consequential damages are excluded.