



TUFFKOTE

PROTECTIVE COATINGS

EPIPLUS 556 SUPERBUILD ST COATING

Data Sheet No. SPL/PMG/20191000078

A two pack polyamide high build mastic surface tolerant coating designed for application on manually cleaned steel surface as well as concrete surface. The product can be applied over most of the tightly adhering aged coatings and recommended as maintenance primer with suitable top coats.

Product Information

Color	Grey and selected colour
Finish	Smooth & Semi-glossy
Flash Point	Above 23° C
Mixing Ratio (By Volume)	Base : Accelerator 1 : 1
Volume Solids	70 ± 3 %
Recommended dry film thickness	75 - 100 microns
Corresponding wet film thickness	110 - 145 microns
Theoretical Spreading Rate	9.33 – 7.0 Sq.metre/litre
Drying time at 30°C	Surface dry : 5 - 10 hours Handleable dry : 16 - 18 hours Hard dry : 24 - 48 hours Full curing : 7 Days
Interval before Over-coating Over-coating	Minimum – 24 hours Maximum – 7 days
Volatile organic Compound (VOC)	250 gm/ltr (EPA 24 method)
Storage Life	12 months minimum at 30°C if stored in dry in sealed container at shaded condition away from heat source and ignition
Dry Heat Resistance	Up to 120°C (Intermittent)

Uses

Maintenance painting for highly corrosive Fertilizer plants, Chemical factories, Refineries, Petrochemical units, Railway Bridges, Marine & Port installations, Drilling Rigs and Platforms and inaccessible areas of complex structure.

Surface Preparation

Steel Surfaces

Surface must be clean, dry & free from contamination. Prior to paint application all surfaces should be assessed and treated in accordance with ISO 8504:2000.

it is recommended to hand tool/ power tool cleaning up St2 or St3 before application of this product

This product is applied on tightly adhered aged/Old Coating

For damage area rectification and concrete coting, please contact the Technical team of Shalimar Paints Limited

Application Details

Method of Application

Brush / Roller /Airless Spray/ Air Spray

Notes on Airless Spray

Tip Range	21 – 29 thou.
Total Output	2100-2500 psi.
Fluid Pressure	(147-196 kg/sq.cm.)
Pot Life	6 - 8 hours
Thinner	Thinner 6756

Notes on Air Spray

Nozzle Orifice – 1.2 mm to 3 mm
Nozzle Pressure – 0.3-0.4 Mpa

Limitations

In common with all epoxies, this product may chalk on exposure. Discolouration also occurs under certain exposure conditions, but this is not detrimental to coating's performance. The product is not recommended for immersion service in acids, alkalis and water.



Typical System Selection Guide

SURFACE	1 ST COAT	2 ND COAT	3 RD COAT	4 TH COAT
Steel	EPIPLUS 556 SUPERBUILD ST COATING	Epigard XL HB MIO Brown/ Grey	Shalithane Finish/ Shalithane HB Finish / Shalithane RC HB Finish / Shalithane Acrylic PU Finish	Shalithane Finish/ Shalithane HB Finish / Shalithane RC HB Finish / Shalithane Acrylic PU Finish
- Do -	-do-	Epigard XL HB MIO Brown/ Grey	Epigard Finish/ Epigard epoxy finish/ Epigard XL HB Finish	Epigard Finish/ Epigard epoxy Finish/ Epigard XL HB Finish
- Do -	-do-	Bipigard CTE XL / Bipigard 580 HB CTE Black	Bipigard CTE XL / Bipigard 580 HB CTE Black/ BIPIGARD COALTAR FINISH	-

Chemical Resistance Guide (with suitable topcoat)

EXPOSURE	Acids	Alkalis	Solvents	Salt	Water
SPLASH & SPILLAGE	Good	Excellent	Good	Excellent	Excellent
FUMES & OUTDOOR EXPOSURE	Good	Excellent	Very Good	Excellent	Excellent

Health & Safety

Use Proper Personal Protective Equipment(PPE) during application of this product.

Please consult Material Safety Datasheet (MSDS)

Precaution

Provide adequate ventilation during application and drying. Clean Spray gun equipment and hose immediately after application of material.

Standard Pack Size

20 litres - For available pack size contact local representative of Shalimar Paints Limited

NOTES:

1. This Product datasheet supersedes all previous datasheet and subject to change without prior notice
2. Do not apply when surface temperature is less than 3 °C than dew point.
3. Mixing with mechanical agitator is strongly recommended
4. Use material within stipulated potlife
5. Do not apply paints when environment temperature rises above 50 °C or when relative humidity rises above 85%. Do not apply during rain, fog or mist.
6. Use of thinners other than supplied or approved by Shalimar may adversely affect product performance
7. Drying is dependent on temperature, relative humidity and thickness; ranges is given for considering those parameters
8. System Guide is a typical and for indicative purpose only, however this can have wide range of combination. For details, please contact Shalimar Paints limited
9. Request for details information of surface preparation, paint application on the recommended coating system

DISCLAIMER: This PDS is by no means a comprehensive data. The company will not be liable for losses or damages howsoever caused including liability for negligence, which may be suffered by the user of the data contained therein. It is the user's responsibility to conduct all necessary tests to confirm the suitability of any product or system for their intended use. No guarantee of result is extended since conditions of use are beyond our control. Liability is limited to replacement of the product hence cost of labour charges or consequential damages are excluded.