



**SHALIMAR
PAINTS**

TUFFKOTE

PROTECTIVE COATINGS

LUSTROTHERM HT 600 SILICONE ALUMINIUM PAINT

Data Sheet No. SPL/PMG/2019100032

A single pack high performance heat resistant aluminium paint based on silicone resin medium for protection of steel surface operating upto 600°C dry heat.

Product Information

Color	Aluminium
Finish	Bright metallic
Flash Point	Above 23°C
Volume Solids	18 ± 2 %
Recommended dry film thickness	15 - 20 microns
Corresponding wet film thickness	83 - 111 microns
Theoretical Spreading Rate	12.0 - 9.0 Sq.m/ltr
Drying time	Dust free - 4 hours
Curing	Apply 1 st coat. Air dry for 24 hrs. Alternatively heat cure @ 200°C for 1 hour after 4 hours of air drying. Apply 2 nd coat. Allow it to dry overnight and then gradually raise the temperature to working temperature.
VOC	740 gm/ltr (EPA Method 24)
Storage Life	12 months minimum @ 30°C if stored in a dry sealed container at shaded condition away from heat source and ignition
Dry Heat Resistance	Upto 600° C (Intermittent)

Surface Preparation

Steel Surface

Surface to be coated should be clean, dry and free from contamination. Prior to paint application all surfaces should be assessed and treated in accordance with ISO 8504:2000.

It is always recommended to apply suitable primer coat before application of this product. Ensure surfaces to be coated is dried and followed overcoating interval and if required sufficiently roughened by emery paper.

This product can be applied over Hand & Power tool cleaning to St2 & St3.

For damage area rectification contact the Technical team of Shalimar Paints limited.

Application Details

Method of Application

Brush / Conventional Spray

Notes on Air Spray

Nozzle Orifice – 0.8 mm to 1.2 mm

Nozzle Pressure – 0.3-0.4 Mpa

Thinner | 6752

Uses

Suitable as topcoat for Chimneys, Flare Stacks, Exhausts, Pipe works, Incinerators and similar surfaces exposed to dry heat attack at 600°C.

Typical System Selection Guide

SURFACE	1 ST COAT	2 ND COAT
Steel	LUSTROTHERM HT 600 SILICONE ALUMINIUM PAINT	
- Do -	LUSTROTHERM HT 600 SILICONE ALUMINIUM PAINT	LUSTROTHERM HT 600 SILICONE ALUMINIUM PAINT

Chemical Resistance Guide (with suitable top coat)

EXPOSURE	Acids	Alkalis	Solvents	Salt	Water
SPLASH & SPILLAGE	poor	poor	Fair	Fair	Fair
FUMES & OUTDOOR EXPOSURE	Good	Good	Good	Good	Good

Health & Safety

Use Proper Personal Protective Equipment(PPE) during application of this product.

Please consult Material Safety Datasheet (MSDS)

Precaution

Provide adequate ventilation during application and drying. Clean Spray gun equipment and hose immediately after application of material.

Standard Pack Size

1,4 & 20 litres - For available pack size contact local representative of Shalimar Paints Limited

NOTES:

1. This Product datasheet supersedes all previous datasheet and subject to change without prior notice
2. Do not apply when surface temperature is less than 3 °C than dew point.
3. Mixing with mechanical agitator is strongly recommended
4. Do not apply paints when environment temperature rises above 50 °C or when relative humidity rises above 85%. Do not apply during rain, fog or mist.
5. Use of thinners other than supplied or approved by Shalimar may adversely affect product performance
6. Drying is dependent on temperature, relative humidity and thickness; ranges is given for considering those parameters
7. System Guide is a typical and for indicative purpose only, however this can have wide range of combination. For details, please contact Shalimar Paints limited
8. Request for details information of surface preparation, paint application on the recommended coating system

DISCLAIMER: This PDS is by no means a comprehensive data. The company will not be liable for losses or damages howsoever caused including liability for negligence, which may be suffered by the user of the data contained therein. It is the user's responsibility to conduct all necessary tests to confirm the suitability of any product or system for their intended use. No guarantee of result is extended since conditions of use are beyond our control. Liability is limited to replacement of the product hence cost of labour charges or consequential damages are excluded.